

## Datenblatt

### PA12-L1600

<u>Property</u>	<u>Typical value</u>
-----------------	----------------------

#### Material specific properties

Melting point	183 °C
Heat Deflection (1,80 MPa)	83,5 °C
Tensile strength	46 MPa
Tensile modulus	1602 MPa
Elongation at break	36 %
Flexural strength	46,3 MPa
Flexural modulus	1300 MPa
Impact strength (unnotched Izod)	13,2 kJ/m <sup>2</sup>